



ButaPhalt® Liquid

An Innovative Crosslinking Additive

PATENT PENDING

TECHNICAL DATA SHEET

TYPICAL PROPERTIES

Property	L6o Performance Grade		L12o Ultra Fast Grade	
Active Ingredients	Nominal 50%		Nominal 50%	
Specific Gravity	1.2 kg/liter	10 lb./gal	1.2 kg/liter	10 lb./gal
Suggested Dosage (by weight of PMB)	0.15% to 0.24%		0.08% to 0.12%	

PRODUCT FORM & PACKAGING OPTIONS

Property	L6o Performance Grade	L12o Ultra Fast Grade
Color	Light Yellow	Light Yellow
Form	Stable Pumpable Liquid Suspension	Stable Pumpable Liquid Suspension
Packaging	Nominal: 1135 liter (300 gal.) totes	Nominal: 1135 liter (300 gal.) totes

WEBSITES & KEY DOCUMENTS

Click on the links below to visit our website and download the latest versions of key documents.

Sripath Website	https://sripath.com/
Safety Data Sheets	https://sripath.com/resources/sds/
Usage Guidelines	https://sripath.com/products/butaphalt/
Environmental Product Declaration	https://sripath.com/sustainability/

For more information contact us at: info@sripath.com



Sripath.com
Americas & Africa



Sripathapc.com
Australia, New Zealand,
& Asia-Pacific Region



SripathInnovations.com
United Kingdom, European Union,
& Middle East



Bitpath.co.in
India

COPYRIGHTS: ©-2026 Jay Holding, Inc.

TRADEMARKS: Sripath®, Sripath Technologies®, the Sripath Technologies Logo®, ReLIXER®, PGXpand®, PGXtend®, NuMIXER®, ReNUBIT®, SriCote®, KoolTEQ™, PHALANX®, ButaPhalt®, ButaChem™, Bitpath®, the Bitpath Logo®, Sripath Asia-Pac®, the Sripath Asia-Pac Logo®, Sripath Innovations®, the Sripath Innovations Logo®, ReJUVN8™, ReGENR8™, Make Asphalt Better®, Make Bitumen Better®, Pioneering Sustainable Roadways®, Bitumen Pathways for the Future®, Chemistry from the Lab to the Field®, and the Rocky Asphalt® and Sandy Asphalt® Mascots are trademarks and/or service marks of Jay Holding Inc. and/or its affiliates in the United States of America and/or in other countries. All Rights Reserved.

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the recipient or user from the responsibility of carrying out own tests, experiments, and validation. The recipient or user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.