



SriCote®

A Superior Anti-Stripping Agent
Extraordinary Performance in
Demanding Paving Environments

A close-up photograph of water splashing on a dark asphalt surface. The water droplets are captured in mid-air, creating a dynamic and textured scene. The background is blurred, showing more of the wet pavement and some greenery in the distance.

*Stronger Adhesion of Aggregates.
Reduce Moisture Damage.
Improve Fuel Resistance.*

Better Bonding

SriCote®, an amine-free anti-strip agent, enhances the bonding between the bitumen and aggregate in a paving Mix, offering improved protection against raveling, rutting, and pothole formation. SriCote helps minimize damage typically caused when road pavements are exposed to moisture and fuel. It improves long-term roadway performance and durability, delivering longer-lasting roadways with smoother rides.

The ability of SriCote® to enhance moisture and fuel resistance of roadways, makes it an ideal additive for demanding applications such as airports and seaports, where pavements are prone to exposure from fuel and liquids. It significantly improves values measured by Wet Strength, Hamburg Wet Wheel Rutting, Aggregate Stripping, and Tensile Strength Retention (TSR) tests. SriCote is highly dosage efficient and is compatible with a wide range of bitumen and Polymer Modified Binders (PMB) from around the globe.

SriCote® is easy to use, safe to handle, smokeless and odorless in hot bitumen, and poses no known health concerns. It does not affect the binder grade. It is stable at the processing and paving temperatures. A liquid at ambient conditions, it is easily pumpable from bulk tanks or totes.

Excellent Fuel Resistance

Property	SriCote®
Dosage, wt % Asphalt	0.35%
Average Air Voids, %	2.9%
Average Fuel Resistance Weight Loss, %	2.0
Marshall Stability After FR, Newtons	2804

Outstanding Moisture Resistance

Property	SriCote®
Dosage, wt % Asphalt	0.35%
Dry Strength, kPa	933.8
Wet Strength, kPa	901.7
TSR	97%

SriCote® Technical Data

Property	Typical Value	
Boiling Point	290° C	554° C
Density	1.1 kg/liter	9.2 lb/gal
Flash Point, COC	> 150° C	> 302° F
Viscosity @ 24° C (75° F)	0.1 Pa.s	100 cp
pH	7	

PACKAGING: Pumpable liquid from IBC totes or drums.
All values representative only.



Sripath.com
(North America, South America, Japan & Africa)

Sripathapc.com
(Australia, New Zealand & Asia-Pacific Region)

SripathInnovations.com
(Europe)

Bitpath.co.in
(India & Middle East)



COPYRIGHTS: ©-2023 Sripath Technologies®, LLC

TRADEMARKS: Sripath®, Sripath Technologies®, the Sripath Technologies Logo®, ReLIXER®, PGXpand®, PGXtend®, NuMIXER®, ReNUBIT®, SriCote®, KoolTEQ™, Bitpath®, the Bitpath Logo®, Sripath Asia-Pac®, the Sripath Asia-Pac Logo®, Sripath Innovations®, the Sripath Innovations Logo®, ReJUVN8™, ReGENR8™, Make Asphalt Better®, Make Bitumen Better®, Pioneering Sustainable Roadways®, Bitumen Pathways for the Future®, are trademarks and/or service marks of Jay Holding Inc. and/or its affiliates in the United States of America and/or in other countries. All Rights Reserved.

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the recipient or user from the responsibility of carrying out own tests, experiments, and validation. The recipient or user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.